



RUSTPREP #40-101 GRAY PRIMER

TECHNICAL DATA

PAGE 1 OF 1

PRODUCT DESCRIPTION

A low odor, fast drying, single component water borne CROSS-LINKED ACRYLIC primer formulated to be used on interior or exterior ferrous, non-ferrous metal, galvanized metal, concrete, masonry or wood surfaces.

RECOMMENDED USES

RUSTPREP #40-101 is recommended for virtually every metal surface. It may be used over new or previously painted iron, steel, and galvanized steel. This product has excellent adhesion and corrosion inhibitive properties.

TECHNICAL DATA

Weight Per Gallon	11.35 lbs
Percent Solid By Weight	60.5%
Percent Solid By Volume	46.3%
Sheen	Flat
Flash Point	Water Base Products Flash Point Over 200° F
Spreading Rate	300-350 Sq/Ft per Gallon
Recommended	Dry Mil Film Thickness 1.5 mil DFT minimum
Drying Time	77° F and 50% Humidity To Touch 15 Minutes
Volatile Organic Content	<50 g/l

PRECAUTIONS

KEEP OUT OF THE REACH OF CHILDREN. Wear protective clothing, gloves and safety glasses. When spraying, a protective mask should be worn to avoid inhalation. Harmful or fatal if swallowed.

ANTIDOTES

INGESTION: Do not induce vomiting. Call a physician.
EYES: Flush with large amounts of water for 15 minutes, holding eyelids open. If irritation persists see a physician.
INHALATION: Remove to fresh air and rest.
SKIN: Wash thoroughly with mild soap and water.

INSTALLATION

PREPARATION

All surfaces must be cured; firm and dry, surfaces should be clean, free of dust, oil, grease and wax. Remove chalky or loose paint, rust, loose mil scale, mildew or any other contamination or condition that would adversely affect the performance of the coating.

APPLICATION

Don not apply if air or surface temperature is below 50°F (10°C) or is likely to fall below 50°F within 2 hours of application.

Packaging: available in one, five and fifty-five gallon containers.

HMIS-

Health:	0
Flammability:	0
Reactivity:	0
Protection:	B

LIMITATIONS

Do not apply over scaled rust or oily surfaces or other surfaces that are glossy, in these cases adhesion problems may be experienced.

WARRANTY

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.

21595 Curtis Street • Hayward, CA 94545
(510) 887-7254 • Fax: (510) 887-5637
www.roofguardcoatings.com

Our products are guaranteed to meet established quality control standards and product specification at the time of shipment. Information contained in our technical data is based on laboratory and field testing, but is subject to change without prior notice. No guarantees of accuracy are given or implied, nor does TRESKO assume any responsibility for coverage, performance or injuries resulting from storage, handling or use of our products. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one year from date of shipment.